

## Hangzhou Easy Electric Wire and Cable Co.,LTD

Add: Room 305, Building 2, No. 380 Fengxin Road, Hangzhou, China

www.eescable.com

## TEST REPORT

Products	AAAC 35		Size	7*2.52	MM2
Standard	ASTMB398 ASTMB399	Invoice No.	20230216003	Date	2023/02/16
NO.	Item	Standards and Requirements		Test Results	Evaluation
1	Conductor				
1-1	Diameter of conductor	7.56±0.1		7.57	Qualified
1-2	Number of Aluminum Alloy wire	7		7	Qualified
1-3	Diameter of Aluminum Alloy wire	2.52±0.03		2.52	Qualified
1-4	Outer Stranding Direction	Rightward		Rightward	Qualified
1-5	Min. breaking load	10.81KN		11.12KN	Qualified
1-6	20℃Max D.C Resistance	≤0.9651		0.9651	Qualified
1-7	Lay Ratio Of Conductor	10-16		13.8	Qualified
1-8	Surface quality of stranded wire	the surface shall be smooth, stranded compactly, no missing, broken, jumping or loosing strands.		Smooth, compact	Qualified
2	Performance of alloy wire				
2-1	Min. Tensile Strength	≥315MPa		344MPA	Qualified
2-2	Elongation(250mm)	≥3.0%		4.6%	Qualified
2-3	20℃Max D.C Resistivity	≤0.032841		0.032716	Qualified
2-4	Wrapping test	Eight turns shall be wrapped round a mandrel of diameter equal to the wire diameter, the wire shall not break		No break	Qualified

Tested by: Shaoqiong He Checked by: Guohui Xu

杭州益睿电线电缆有限公司 BANGZHOU EASY ELECTRIC VIRE AND CABLE CO., LTD.