

Hangzhou Easy Electric Wire and Cable Co.,LTD

Add: Room 305, Building 2, No. 380 Fengxin Road, Hangzhou, China

www.eescable.com

TEST REPORT

					1	
Products	AAC ASTN		Size	900MCM		
Standard	37/3.96	Invoice No.	20230228003	Date	2023.2.28	
NO.	Item	Standards and	Requirements	Test Results	Evaluation	
1	Structure					
1-1	Number Of AL Wire	37		37	Qualified	
1-2	Number Of Steel Wire	1		1	Qualified	
1-3	Diameter Of Conductor	27.74±0.28		27.73	Qualified	
1-4	20℃ Max D.C Resistance	≤0.0631 Ω /km		0.06119	Qualified	
1-5	The direction of outer layer	Right- handed		Right- handed	Qualified	
2	Surface Of Conductor					
2-1	Surface Quality	The Surface Shall Be Smooth, Stranded Compactly, No Missing, Broken, Jumping or Loosing Strands.		Smooth, Compact	Qualified	
3	Aluminum Wire Properties					
3-1	Material	Hard drawn a	luminum wire	Hard drawn aluminum wire	Qualified	
3-2	Diameter Of AL Wire	37/3	.96	37/3.96	Qualified	
3-3	Min. Tensile Strength	170N,	/mm2	181	Qualified	
3-4	Resistivity at 20℃	≤0.02	28264	0.027824	Qualified	
3-5	Elongation in 10 in	1.6		2.0%	Qualified	
4	Steel Wire Properties					

Hangzhou Easy Electric Wire and Cable Co.,LTD

Add: Room 305, Building 2, No. 380 Fengxin Road, Hangzhou, China



Hangzhou Easy Electric Wire and Cable Co.,LTD

Add: Room 305, Building 2, No. 380 Fengxin Road, Hangzhou, China

www.eescable.com

4-1	Diameter Of Steel Wire		1	Qualified
4-2	Min. Tensile Strength	55000N/mm2	55687	Qualified
4-3	Min.stress at 1% elongation	/		Qualified
4-4	Elongation	≥3%	8%	Qualified

Tested by: Shaoqiong He

Checked by: Guohui Xu

杭州益睿电线电缆有限公司 BANGZHOU EASY ELECTRIC VIRE AND CABLE CO., LTD.