

## Hangzhou Easy Electric Wire and Cable Co.,LTD

Add: Room 305, Building 2, No. 380 Fengxin Road, Hangzhou, China

www.eescable.com

## TEST REPORT

| Products | AAAC Anaheim                       |  | Size        | 7*3.78MM2             |            |
|----------|------------------------------------|--|-------------|-----------------------|------------|
| Standard | ASTMB398 ASTMB399                  | Invoice<br>No.   | 20220910003 | Date                  | 2022/09/10 |
| NO.      | ltem                               | Standards and Requirements   |             | Test Results          | Evaluation |
| 1        |                                    | Conductor  |             |                       |            |
| 1-1      | Diameter of conductor              | 11.34±0.12   |             | 11.35                 | Qualified  |
| 1-2      | Number of Aluminum Alloy wire      | 7  |             | 7                     | Qualified  |
| 1-3      | Diameter of Aluminum Alloy<br>wire | 3.78±0.038   |             | 3.79                  | Qualified  |
| 1-4      | Outer Stranding direction          | Rightward  |             | Rightward             | Qualified  |
| 1-5      | Min. breaking load                 | 23.75KN  |             | 23.98KN               | Qualified  |
| 1-6      | 20℃Max D.C Resistance              | ≪0.4244  |             | 0.4210                | Qualified  |
| 1-7      | Lay Ratio Of Conductor             | 10-16  |             | 13.5                  | Qualified  |
| 1-8      | Surface quality of stranded wire   | the surface shall be smooth,<br>stranded compactly, no<br>missing, broken, jumping or<br>loosing strands.              |             | Smooth,<br>compact    | Qualified  |
| 2        | Performance of alloy wire          |  |             |                       |            |
| 2-1      | Min. Tensile Strength              | ≥315MPa  |             | 323MPA                | Qualified  |
| 2-2      | Elongation(250mm)                  | ≥3.0%  |             | 3.8%                  | Qualified  |
| 2-3      | 20℃Max D.C Resistivity             | ≤0.032841  |             | 0.032713              | Qualified  |
| 2-4      | Wrapping test                      | Eight turns shall be wrapped<br>round a mandrel of diameter<br>equal to the wire diameter, the<br>wire shall not break |             | e <sup>No break</sup> | Qualified  |

Tested by: Shaoqiong He

Checked by: Guohui Xu



Hangzhou Easy Electric Wire and Cable Co.,LTD

Add: Room 305, Building 2, No. 380 Fengxin Road, Hangzhou, China