

Hangzhou Easy Electric Wire and Cable Co.,LTD

Add: Room 305, Building 2, No. 380 Fengxin Road, Hangzhou, China

www.eescable.com

TEST REPORT

Products	AAAC Butte		Size	312.8MCM	
Standard	ASTM B 399	Invoice No.	20230707001	Date	2023/07/7
NO.	Item	Standards and Requirements		Test Results	Evaluation
1	Conductor				
1-1	Diameter of conductor	$16.3\text{mm}\pm0.17$		16.3	Qualified
1-2	Number of Aluminum Alloy wire	19		19	Qualified
1-3	Outer Stranding direction	Rightward		Rightward	Qualified
1-4	Min. breaking load	46.45KN		53.405KN	Qualified
1-5	20℃Max D.C Resistance	\leq 0.2113 Ω /km		0.2086	Qualified
1-6	Grease	IEC Case 3		IEC Case 3	Qualified
1-7	Finished weight	435kg±8.7		441	Qualified
1-8	Surface quality of stranded wire	the surface shall be smooth, stranded compactly, no missing, broken, jumping or loosing strands.		Smooth, compact	Qualified
2	Performance of alloy wire				
2-1	Diameter of Aluminum Alloy wire	3.26mm±0.033		3.26	Qualified
2-2	Min. Tensile Strength	≥315MPa		330MPA	Qualified
2-3	Elongation(250mm)	≥3.0%		7%	Qualified
2-4	20℃Max D.C Resistivity	≤0.032841		0.03157	Qualified
2-5	Wrapping test	Eight turns shall be wrapped round a mandrel of diameter equal to the wire diameter, the wire shall not break		No break	Qualified

Tested by: Shaoqiong He Checked by: Guohui Xu